



SCUDOTENE BV ALU

- 20 °C

Characteristics	Norms	U.M.	Test results	Tolerance
			SCUDOTENE BV ALU	
Norms	/	/	EN 13970	/
Carrier type	/	/	Fiberglass and aluminium foil	/
Compound	/	/	BPE - Elastomeric bitumen / BPE Adhesive	/
Upper surfacing	/	/	Film PE	/
Lower surfacing	/	/	Removable siliconized film	/
Type of application	/	/	BV-Vapour barrier	/
Method of application	/	/	Self-adhesive	/
Visible defects	EN 1850-1	-	Pass	/
Length	EN 1848-1	m	≥ (16 m -1%) per 1,5 and 2 mm ≥ (10 m -1%) per 3 mm	/
Width	EN 1848-1	m	≥ 1 m -1%	/
Straightness	EN 1848-1	-	Pass	/
Thickness	EN 1849-1	mm	1,5 - 2 - 3	± 0,2
Watertightness (metodo B - 60 kPa)	EN 1928	-	Pass	/
External fire performance	EN 13501-5	-	F roof	/
Reaction to fire	EN 13501-1	-	EUROCLASS E	/
Shear resistance of joint - heat lap - side lap	EN 12317-1	N/50 mm	400 300	- 20% - 20%
Tensile properties -maximum longitudinal tensile strength -maximum transversal tensile strength - longitudinal elongation - transversal elongation	EN 12311-1	N/50 mm N/50 mm % %	500 400 4 4	- 20% - 20% - 2 pp - 2 pp
Resistance to impact	EN 12691	mm	NPD	/
Resistance to static loading	EN 12730	kg	NPD	/
Resistance to tearing (nail shank) - longitudinal - transversal	EN 12310-1	N	70 70	-30% -30%
Dimensional stability	EN 1107-1	%	NPD	/
Flexibility at low temperature	EN 1109	°C	- 20	/
Flow resistance at elevated temperature	EN 1110	°C	100	/
Artificial ageing by long term exposure to elevated temperature	EN 1296 + EN 1109	°C	- 15	+ 15°C
Water vapour transmission properties	EN 1931	-	μ = 1.500.000	- 10%

REV 01/18

TECHNINCOL ITALIA srl reserves the right to modify the technical data in this specification sheet which is based on current production without prior warning.

All indications in this specification sheet are based upon our experience and current working practices.

TECHNINCOL ITALIA s.r.l.

Via Galoppat, 134 – 33087
Pasiano di Pordenone (PN), Italia
P.IVA 01745250934 - REA PN - 101202
Tel.: 0434-614611, Fax: 0434-628178
www.technincol.it, info@technincol.it